

TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

adds TROTON SPRAY RUST FILLER EPOXY



PRODUCT DESCRIPTION

RUST FILLER SPRAY it is a primer and rust converter in one, made from high quality epoxy resin. Product has very good anti-corrosive properties. Create a uniform coating provides excellent protection against harmful weather conditions. Compatible with all standards fillers, putties and lacquers (except nitro products). To use with 2K lacquers we recommend a compatibility test. Product is free of heavy metals and mineral acids, has very high solvent-resistance.

PHISICAL AND CHEMICAL PROPERTIES

- Base : epoxy resin
- Capacity : 400 ml
- Color: amber
- Density: 0,79 g/ml (20⁰C)
- Drying time*:
 - Dust – dry after 1 hour
 - Coatable: after approx. 6 hours
- Efficiency of 100 ml. approx. 0,4 m²
- Temperature resistance: up to 80⁰C

*in temperature 20⁰C and relative air humidity 50%

CONTENT OF VOLATILE MATTER

VOC = 697,5 [g/l]

This product satisfies requirements of the European Union Directive (2004/42/WE), which for this product category (B/5) gives the limit value of content of volatile matter at the level of 840 [g/l] of the ready-for-use product.

USAGE

- Best processing temperature is 10 ÷ 25⁰C.
- Before using shake aerosol can for about 3 minutes.
- Surface to be treated should be clean from rust, dirt, paint flakes and degreased.
- Spray from a distance of approximately 25 cm. from treated surface.
- Apply 3 – 4 layers (depending on corrosion degree).
- Stoving of element makes product more resistant. Let the coat dry for 15 min. and then stove for 15 min. at max. 160⁰C.
- **After use clean aerosol's outlets** – hold down aerosol's valve, push the bottom and release contents for 5 seconds.

Caution: For safety reasons always comply with information provided in the Material Safety Data Sheet

STORAGE

Store the product components in sealed container, in dry and cool places, away from heat sources, as well as direct sunlight.

EXPIRY DATE

5 years from the production date.

All information are based upon the precise laboratory studies and many years of experience. The good market position does not release us from the constant supervision of our products quality. However we are not responsible for the final effects of the improper storage or application of our products, as well as for work inconsistent with the good craft practice.

TROTON Sp. z o.o.
Ząbrowo, Poland