

# **TECHNICAL INFORMATION**

## FOR PROFESSIONAL USE ONLY

# adds Troton ANTI GRAVEL SPRAY - UBS

# **PRODUCT DESCRIPTION**

Product based on synthetic resins designed to protect car bodies against the harmful effect of the weather conditions, fuel, oil, water and salt. Product creates a strong, flexible anti-gravel layer, also has a soundproofing and anticorrosive properties. Can be coated with any lacquer systems. Doesn't contains bitumen.

#### PHYSICAL AND CHEMICAL PROPERTIES

Color: black, white, grey

Capacity: 500 ml.

• Glass grade: matt

Drying time in 20°C:

- dust dry after approx. 30 min.

tack free after approx. 60 min.

- re-sprayable after approx. 2 hours

# **VOLATILE COMPONENTS CONTENT**

VOC = 579 [g/l].

The product fulfils the requirements of the European Directive (2004/42/WE), which defines the volatile components content for that products category (cat. B/5) at the level of 840[g/l] for the ready product.



## SUBSTRATE AND SURFACE PREPARATION

The product is used for cleaning substrates:

- polyester laminates
- polyester putties
- epoxy primers
- two-component acryl fillers
- steel substrates,
- steel rustless surfaces
- aluminium substrate,
- plastic materials
- wash primer

The polyester laminates should be degreased, dry ground (P80-P120) and degreased again.

The polyester putty should be degreased, dry ground (P120).

The substrates should be degreased, dry ground (P220 – P280) and degreased again.

The stainless material should be degreased.

The steel surface should be degreased, dry ground (P80 – P120) and degreased again.

The aluminium and galvanized surface should be degreased, dulled with the abrasive cloth and degreased again.

The old coatings should be degreased, dry ground (P220 – P280) and degreased again.

The plastic surface should be clean by water and detergent, dulled with the abrasive cloth and degreased again.

On plastic it is recommended to hold it at temperature of 50°C, with is useful to remove silicones from the surface.

## **USAGE**

- Best temperature application 15-25 °C.
- Shake the bottle before use 2 min and try spray on cardboard.
- Spray the surface from a distance of about 25-30 cm. Apply 2-3 layers of the agent on time 2-5 minutes. Before another layer shake the bottle.
- Clean the spray nozzle after use! Holding the can with the valve pointing downward, press the button emptying the content for about 5 seconds.

In case of direct application on steel surface recommended imposition of the top layer of lacquer or enamel..

<u>Caution</u>: To maintain safety, always follow the instructions given in the Safety Data Sheet for the given product.



STORAGE		

Store the product components in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight.

# WARRANTY PERIOD

5 years from the production date.