

TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

addsTROTON 2 in 1 ANTI GRAVEL / SEAM SEALANT

PRODUCT DESCRIPTION

Product is based on rubber and synthetic resin, designed to protect car bodies against mechanical damages, rust and harmful effect of the weather conditions, and also seal joints and welds using the spray gun. Sealant has also soundproofing properties. After drying can be covered with all conventional lacquer systems.

PHYSICAL AND CHEMICAL PROPERTIES

- Color: black, grey, white
- Density*: 1,21 – 1,25 kg/l
- Capacity: 1 ltr
- Efficiency: $\pm 0,7 \text{ kg/m}^2$ ($\pm 600 \mu$ wet layer)
- Temp. resistance (after curing): - 25⁰C do +80⁰C
- Viscosity (Brookfield)*: 4,250 m.Pa.s

Drying time*:

- Touch dry: approx. 45 min. ($\pm 700 \mu$)
- Completely dry: approx. 3,5 h. ($\pm 700 \mu$)

* temp. 20⁰C, RH 65%

CONTENT OF VOLATILE COMPONENTS

VOC = 560 [g/l]

This product complies with Directive 2004/42/EC that for this category of products (cat.B/5) provides the threshold value of volatile components' share at the level of 840 [g/l] in the ready for use product.

USAGEAntigravel coating

- Covered surface should be clean, free of dust, grease and rust.
- Shake well can before use.
- Product can be applied using gun with an air-pressure of 3 -6 bar.
- Recommended spraying distance is about 30 cm.
- If the intention is to obtain a thicker coating it is recommended to dry the layers in between.
- Equipment and contaminated surface can be cleaned in fresh condition with solvents. After curing product can be remove only mechanical.
- Depends of the thickness of the coating, after about 60 - 90 minutes surface can be covered by 2k or basecoat lacquers. Before use of 2k lacquers it is recommended to use a primer according to instruction of paint supplier.

Sealing

- Covered surface should be clean, free of dust, grease and rust.
- Shake well can before use.
- Product can be applied using gun with an air-pressure of 2 - 4 bar.
- Recommended spraying distance is about 1 - 2 cm.
- If the intention is to obtain a thicker coating it is recommended to dry the layers in between.
- Equipment and contaminated surface can be cleaned in fresh condition with solvents. After curing product can be remove only mechanical.
- Depends of the thickness of the coating, after about 3 hours surface can be covered by 2k or basecoat lacquers. Before use of 2k lacquers it is recommended to use a primer according to instruction of paint supplier.

STORAGE

Store the product in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight. Storage temperature 10 - 30°C.

WARRANTY PERIOD

2 years from production date.

All information are based upon the precise laboratory studies and many years of experience. The good market position does not release us from the constant supervision of our products quality. However we are not responsible for the final effects of the improper storage or application of our products, as well as for work inconsistent with the good craft practice.

TROTON Sp. z o.o.
Ząbrowo, Poland.

